

TECHNICAL INFORMATION C9/0508

## vitroflex® IRIDISCENT features

Vitroflex IRIDISCENT is a translucent methacrylate cast sheet with a metallic effect on one face.

### PROPERTIES

---

- The IRIDISCENT range provides a special effect, wherein the piece surface is white with metal reflections by impinging light on one face, and when it's illuminated by back takes a smooth coloration completely different to the colour reflected by the metallic particles.
- The particle size and its concentration are variables according to the desired effect.
- The pigment that provides the metallic effect is incorporated in the methacrylate is not a coating as paint.
- Developed for use out-doors limited to moderate climatic conditions and exposure to the sun.
- It is easily machined.
- It can be polished to give a total brightness.
- It can be slightly cold bent.
- It can be thermoformed.
- Lighter than other materials.
- High impact resistance.
- Low thermal conductivity.

### APPLICATIONS

---

- Decorative pieces (gifts, flower shops, hotels, etc.)
- Signage.
- Railings, screens and divisions.
- Furniture.
- Façade panels.
- Wall cladding.

- Skylights, domes.
- Lamps.

## OPERATION

---

- It can be stuck, bended, thermoformed, perforated, polished, milled, etc. just as the standard quality Vitroflex.
- The protective film can be kept during the entire production line, including the thermoformed.<sup>1</sup>

## MAINTENANCE

---

- As its surface is compact and not porous, it can be easily cleaned using a gentle soap solution (neutral pH) with warm water and a nonabrasive cloth. The use of aggressive detergents with non-neutral pH can reduce the service life.
- If an adequate disinfection is required, it is advisable to refer to the table of chemical resistance of Vitroflex, test a piece with no value, and preferably use the manufacturer recommended products only.
- The use of glass washers with alcohol or other similar products may negatively affect the properties and reduce the service life.
- In case the surface has small scratches due to the daily use, they can be removed using a specific polish for car bodies that is used manually. If deep scratches appear or if it is necessary to polish large surfaces, it is advisable to use an orbital eccentric polishing machine.

## RANGE

---

- Size:
  - They are manufactured in 2030 x 1540 mm.
  - Custom-cut sizes can be supplied.

---

<sup>1</sup> It is advisable to run previous tests because heating temperatures and timing should be adjusted in order to get optimum results.

- Colours<sup>2</sup>:
  - The metal particles may have different sizes according to the desired effect.
    - WHITE / RED B750KN
    - WHITE / GREEN B752KN
    - WHITE / GOLD B754KN
    - WHITE / BLUE B756KN
  
- Thickness:
  - The standard thickness is 3 mm.

## QUALITY

---

- In compliance with the rule ISO 7823/1 applicable to methacrylate cast sheets.
- All pieces are controlled.
- Use of high quality shining pigments with maximum resistance to ageing.
- The incorporated pigments are physiologically innocuous, and do not pollute as they are not water soluble and are free of heavy metals. They are not combustible or autoinflammable. They do not conduct electricity and can withstand very high temperatures.

## OTHER AVAILABLE INFORMATION

---

- Table of resistance for various chemical products.
- "Safety Data Sheet" for operation.
- Technical specifications of colours.

---

<sup>2</sup> Other colours can be provided at request.

# Vitroflex IRIDISCENT

## TECHNICAL FEATURES ISO 7823-1<sup>3</sup>

| <b>Physical properties</b>  |                          |                   |            |
|---|--------------------------|-------------------|------------|
| Relative density - Volumetric mass (A Method)   | 1,19                     | g/cm <sup>3</sup> | ISO 1183   |
| Water absorption (Method 1)   | 0,3                      | %                 | ISO 62     |
| <b>Mechanical properties</b>  |                          |                   |            |
| Tensile strength (Type 1 Test, B speed)   | 72                       | MPa               | ISO 527    |
| Traction elasticity module (Type 1 Test, B speed)   | 3000                     | MPa               | ISO 527    |
| Elongation at break (Type 1 Test, B speed)  | 5                        | %                 | ISO 527    |
| Impact strength. Charpy method  | 17                       | KJ/m <sup>2</sup> | ISO 179/2D |
| Rockwell hardness (M Scale)   | 100                      |                   | ISO 2039/2 |
| Bending strength  | 100                      | MPa               | ISO 178    |
| <b>Electrical properties</b>  |                          |                   |            |
| Specific resistance   | >10 <sup>15</sup>        | Ohm               | DIN 53458  |
| Volume resistance   | >10 <sup>15</sup>        | Ohm.cm            | DIN 53458  |
| Dielectric constant<br>a) 50 Hz<br>b) 0,1 Hz  | 3,6<br>2,8               |                   | DIN 53483  |
| <b>Thermal properties</b>   |                          |                   |            |
| Coefficient of linear expansion   | 70,6.10 <sup>-6</sup>    | K <sup>-1</sup>   | EN 2155-12 |
| VICAT softening temperature   | 105-120                  | °C                | ISO 306    |
| Bending temperature under load (A Method, 1,8 MPa)  | 105                      | °C                | ISO 75     |
| Dimension variation at elevated temperatures (shrinkage)  | 2,3                      | %                 | Annex      |
| <b>Optical properties</b>   |                          |                   |            |
| Light transmittance<br>a) Total light transmission at 380-780 nm<br>b) Light transmission at 420 nm<br>c) Light transmission at 420 nm after 1000 hours in the xenon lamp | It depends on the colour | %                 | ISO 2857   |
| HAZE turbidity value  | Does not apply           | %                 | EN 2155-9  |
| Refractive index n <sup>0</sup> (A Method)  | Does not apply           | -                 | ISO/R 489  |

<sup>3</sup> The values of this table refer to the sample of Vitroflex MCI100NN0030. Typical values are not intended for the design.

**Important:** *The information and statements included are believed to be reliable; however, they should not be interpreted as a guarantee or representation that Polimer Tecnic assumes the legal responsibility.*

*Users must perform all verifications and tests as appropriate to determine the particular suitability of any information or product mentioned in this document. Polimer Tecnic cannot guarantee the competence of the material for any particular purpose.*

*Nothing in this document may be interpreted as a permission, incentive or recommendation to operate any patented invention without a license.*

---